

VAN PPC L ONDERVLOEREN


PPC POLYURETHAAN ONDERVLOER 2,0 MM ARTIKELNUMMER 86145

EIGENSCHAPPEN

- Zeer stabiel, geschikt voor alle type klikverbindingen
- Permanent elastische ondervloer bestaande uit minerale vulstoffen en polyurethaanbindmiddelen
- Perfect geschikt voor vloerverwarming 0,01 m2 K/W
- Vochtwerend (naden afplakken)
- Loopgeluidreductie: tot 25%, gemeten volgens EPLF WD 021029-5
- Hoge reductie contactgeluid
- 1,6 kg/m², 16 kg/rol
- Bestaat voor 90% uit natuurlijke grondstoffen
- Bevat geen weekmakers en geen oplosmiddelen of andere schadelijke stoffen

VOLDOET AAN DE EPLF-NORM VOLGENS CEN/TC 16354

		Result
Punctual Comformability	PC	1,05 mm
Compressive Strength	CS	220 kPa
Compressive Creep	CC	48 kPa
Dynamic Load	DL ₂₅	> 2.500.000
Thermal Resistance	R	0,01 m2 K/W
Water vapor diffusion resistance (Sd-value)	SD	> 75 m
Reaction to fire according to EN 13501-1	RTF	Bfl-S1
Resistance to Large Ball	RLB	75 cm
Impact Sound Reduction	IS _{lam}	18 dB
Reflected Walking Sound Reduction	RWS	Tot 25%
Fulfills minimum requirements of EPLF		



PPC POLYURETHAAN ONDERVLOER 2,0 MM ARTIKELNUMMER 86145

ROL: 10 x 1 meter
DIKTE: 2,0 MM